



BOSTON II

A GP lens material suited for daily wear use. Available in a wide range of parameters to suit most fitting situations.

Indications/Features

- Myopia
- Hyperopia
- Astigmatism
- Daily wear



Trade name: Boston II

Material	itafocon A	Saline Absorption	1.0 %
Oxygen Permeability (Dk)	12*	Refractive Index	1.471
Wetting Angle (Captive Bubble)	20 deg.	Specific Gravity	1.13
Hardness (Rockwell R)	119	Tint	Blue

* Polarographic method (ISO/Fatt)

