



## STARSOFT 40 UV

Each of the products has their own benefit, the lower water content materials have greater lens stability and higher tensile strength and suit daily wear applications. The mid water content materials offer a greater Dk that leads to more comfortable wearing characteristics and excellent clarity of vision.

### Technical information

Material Characteristics:

Material	Polymacon 38 % Hema	Ion or Non-Ionic	Non-Ionic
Water content	38%	Elongation to break	136%
UV blocker	Yes	Usage time	6 months
Handling tint	Clear	Material belonging according to the FDA	I
DK	$13 \times 10^{11}$	Manufacturing	Lathing
Light transmission	> 96 %	CE	Approved

