



## Starsoft 59 GM Advance UV

The mid to high water content materials offer a greater Dk that leads to more comfortable wearing characteristics and excellent clarity of vision. Owing to the level of water content in the 75% materials this offers opportunities in bandage and other therapeutic lens applications.

### Technical information

#### Material Characteristics

Material	Contaflex GM Advance	Ionoc or Non-Ionic	Non-Ionic
Water content	60%	Coloring	Yes
UV blocker	Yes	Usage time	6 months
Handling tint	Clear	Material belonging according to the FDA	Filcon II2
DK	30x10 <sup>-11</sup>	Manufacturing	Lathing
Light transmission	>94%	CE	Approved

Star-Lens AB • Box 170 • SE-662 24 Åmål

Tel +46 (0)532 607980 • Fax + 46 (0)532 185 25 • [bestallning@starlens.se](mailto:bestallning@starlens.se)

[www.starlens.se](http://www.starlens.se)